

Technical Bulletin # 859D

Product Description

IMPAX IXT-59 is an aromatic hydrocarbon solvent used for general epoxy cleanup of tools and equipment used for mixing and applying epoxy materials. It must be used before the epoxy has set. Formerly known as PRT-59, IXT-59 is also used for removing grease, oil and other contaminants from surfaces prior to applying epoxy materials.

Application Instructions

WARNING: IXT-59 Solvent causes skin irritation on prolonged contact and may cause eye irritation. Wash hands with soap and water immediately after cleaning up with IXT-59.

CAUTION: IXT-59 is FLAMMABLE.

Physical Properties

DENSITY	7.66 lb./gal. - (0.9 gr/cc)	ASTM C-581
FLASH POINT	89°F (31.7°C) Tag Closed Cup	ASTM C-582
POUR POINT	-139°F (-95°C)	ASTM D-2568

Product Information

PACKAGING / WEIGHT per Unit:	1 gallon – 8 lbs. (3.6 kg)
	5 Gallon – 40 lbs. (18 kg)
SHELF LIFE:	24 months in closed container

Date 01/2011

General: Every reasonable effort is made to insure the technical information and recommendations on these data pages are true and accurate to the best of our knowledge at the date of issuance. However, this information is subject to change without notice. Prior versions of this publication are invalid with the release of this version. Products and information are intended for use by qualified applicators that have the required background, technical knowledge, and equipment to perform said tasks in a satisfactory manner. Consult your local distributor for product availability, additional product information, and technical support.

Warranty: ITW Philadelphia Resins, a division of Illinois Tool Works Inc., warrants that its products meet their printed specifications. This is the sole warranty. This warranty expires one year after product shipment.

Warranty Claims: If any product fails to meet the above, ITW Philadelphia Resins will, at its option, either replace the product or refund the purchase price. ITW Philadelphia Resins will have no other liability for breach of warranty, negligence, or otherwise. All warranty claims must be made in writing within one year of the date of shipment. No other claims will be considered.

Disclaimer: ITW Philadelphia Resins makes no other warranty, expressed or implied, and specifically disclaims any warranty of merchantability or fitness for a particular purpose.

Suggestions concerning the use of products are not warranties. The purchaser assumes the responsibility for determining suitability of products and appropriate use. ITW Philadelphia Resins' sole liability, for breach of warranty, negligence or otherwise, shall be the replacement of product or refund of the purchase price, at ITW Philadelphia Resins' election. Under no circumstances shall ITW Philadelphia Resins be liable for any indirect, incidental or consequential damages.

Modification of Warranty: No distributor or sales representative has the authority to change the above provisions. No change in the above provisions will be valid unless in writing and signed by an officer or the Technical Director of ITW Philadelphia Resins. No term of any purchase order shall serve to modify any provision of this document.

Mediation and Arbitration: If any dispute arises relating to products or product warranties, either the purchaser or ITW Philadelphia Resins may a) initiate mediation under the then current Center for Public Resources (CPR) Model Procedure for Mediation of Business Disputes, or b) initiate a non-binding arbitration under the rules of the American Arbitration Association for the resolution of commercial disputes.